

	EMBOSSED VACUUM BAGS FILM	
--	--------------------------------------	--

BASIC DATA	PAPE	100 ³	µm
Composition and thickness	PA polyamide	20	µm
	PE polyethylene	80	µm
Total substance		96,4	g/m ²

Tolerances on the compositions (Thickness and weight: ± 10%)

Substance average/side	g/m ²			89,7
Tensile strength at break (Average)	N/15 mm	DIN EN ISO	ld ¹	>40
		527-1, -3	cd ²	>30
Elongation at break (Average)	%	DIN EN ISO	ld	>200
		527-1, -3	cd	>250
Seal strength	N/15 mm		150 °C / 5 bar / 1,0 sec.	≥ 25

PERMEABILITY³

Oxygen permeability	cm ³ /m ² /d/bar	DIN 53380	23 °C / 0% R.H.	50
Water vapor transmission rate	g/m ² /d	DIN 53122	23 °C / 85% R.H.	3

Food law compliance: CE : 10/2011, 1935/2004, 1895/2005 and D.M. 21/03/1973 and DPR 777/82, and updates.

NOT SUITABLE FOR PASTEURIZATION.

STORAGE ARRANGEMENTS:

Store in a cool, dry place, away from heat, not kept in warm storage areas or direct sunlight. It is recommended 10 - 30 °C temperature range, 40 - 60% RH.

All data is based on the best of our knowledge, the values are derived from a limited number of samples. The instructions below are indicative.

ld = longitudinal traction

cd = cross traction

³The values corresponds to the film not embossed

SALG OG SERVICE AF:

Flowpakkemaskiner
 Dybtrækmaskiner
 Traysealere
 Vejesystemer
 Krympepakkeanlæg
 Vertikale posepakkemaskiner
 Vacuumpakkemaskiner

EMBALLAGE:

Vacuum-, koge-
 samt krympeposer
 Flexible folier
 Krympefolier
 Micro- og macro OPP folier
 PE-folie

SALGS- OG LEVERINGSBETINGELSER:

For alle leverancer
 af nye og brugte maskiner
 samt emballage er
 omstående salgs- og
 leveringsbetingelser
 gældende.

BANK:

Danske Bank A/S Copenhagen
 Reg. nr.: 4597
 Konto nr.: 4354621
 IBAN: 6430000004354621
 SWIFT-BIC: DABADKKK

